

Wireless, Dual-Type Coating Thickness Tester Model LZ-200W

Wireless Model



Electromagnetic Coating Thickness Tester

Model LE-200J



Superior technology supported the development of the world's first wireless probe coating thickness testers. All measurement data is transferred from the probe to the main unit, which is capable of storing up to 1,500 data entries.

Specifications

opcomoducino	
Measurement principle	Dual Electromagnetic / Eddy-current
Applications	Non-magnetic coatings on iron and steel (magnetic metal)
	Substrates and insulating coatings on non-mag-
	netic metal substrates
Measurement range	Electromagnetic Type: 0 ~ 1500mm or 60.00mils
	Eddy-current Type: 0 ~ 800mm or 32.00mils
Measurement precision	Electromagnetic type: ±0.3mm (absolute error) under
	50mm ±2% (relative error) at or above 50mm
	Eddy-current type: ±0.1mm (absolute error) un-
December 19	der 50mm ±3% (relative error) at or above 50mm
Resolution	0.1mm under 100mm, 1mm over 100mm
Number of calibration	4 Electromagnetic type, 4 Eddy-current type
Memory capacity	1500 coating thickness measurements maximum
Statistical functions	Number of measurements, average value, standard devia-
E level e le l	tion, maximum value, minimum value, block numbers
External output	Standard RS-232C (transmission speed 2400bps)
Power source	Main Unit: 100V AC or 9V DC (10 size "AA" alkaline bat-
	teries, 6 batteries for circuit section and 4 for the printer
Dottory life anon	section.) Probe: 7.5V cylinder battery 2CR 1/3 (Uses 1)
Battery life span	Main unit: 30 hours Probe: 14 hours
Operating temperature range	$0 \sim +40^{\circ}C$
Dimensions & Weight	Main Unit: 140(W) x 250(D) x 80(H) mm 1.1kg Probe: 26(W) x 38(D) x 134(H) mm 0.08kg
	Shipment: 4.0kg
Accessories	Iron substrate (1), infinite adjustment dummy (1), cali-
Accessories	bration plates (1 set of 6), size "AA" alkaline batteries
	(10), 2CR 1/3 cylinder battery (1, VZ-200W has two
	sets worth), button battery holder (1, LZ-200W has two
	sets worth), User's Manual, Probe Adapter (1), AC
	adapter (1), printer paper (2)
Options	Probe connection cable, computer connection cable.
Optionio	1 1000 commodition dubito, computer commodition dubito.

The LE-200J is a portable coating thickness tester with a built-in printer. This unit can accurately and quickly measures many items such as magnetic plating (electrolyzed nickel plating not included), coating, painting, and lining without injuring or damaging the item. Furthermore, you can print out the measurement results on-site with the internal printer.

Specifications

Measurement Method	Electromagnetic induction
Applications	Non-magnetic coating on iron and steel (ferrous)
	substrates
Measurement Range	0-1500µm or 60.00mils
Measurement Precision	Under 15 μ m: $\pm 0.3\mu$ m, 15 μ m or greater: $\pm 2\%$
Resolution	0.1μm (less than 100μm), 1.0μm (100μm or greater)
Statistical Functions	Number of measurements, Average value, Stan-
	dard deviation, Maximum value, Minimum value,
	Block numbers
Probe	One-point contact fixed pressure (LEP-J)
Display Format	Digital(LCD, smallest displayed unit 0.1µm)
Output	RS-232C interface(transmission speed-2400bps)
Power Source	AC100V (50/60Hz) or 1.5 ("AA" size Alkaline bat-
	teries) x 6 (main unit), Printer ("AA" size Alkaline
	batteries) x 4
Dimensions & Weight	120(W)x250(D)x55(H)mm, 1.0kg
	Shipment 2.5kg
Accessories	Calibration plate, Iron substrate, Batteries (1.5V,
	"AA" size Alkaline), Probe adapter, AC adapter,
	Printer paper, Carrying case
Options	L Probe LEP-21L(Probe for use on the inside sur-
	face of pipes), Data Management Software
	"McWave Series" and "MultiProp"
	(McWave Series and MultiProp are products of CEC Co.)